




HOW TO READ A UL BLUE CARD.



Plastics for Additive Manufacturing
[Guide Information](#)

ABC Company
333 Pflingsten Rd Northbrook, IL 60062 USA

Filament ABC
Polyetherimide (PEI), furnished as filaments

Process Category: Material Extrusion

E12345

View Blue Card Format

Color	Min Thk (mm)	Flame Class	HWI	HAI	GWIT	GWFI	RTI Elec	RTI Imp	RTI Str
NC	1.5	V-0	-	-	750	960	50	50	50
	3.0	V-0	-	-	850	960	50	50	50


Comparative Tracking Index (CTI): 0 Dielectric Strength (kV/mm): 15 High-Voltage Arc Tracking Rate (HVTR): 1 IEC Comparative Tracking Index (Volts Max): 600	Inclined Plane Tracking (IPT) kV: 1 Volume Resistivity (10x ohm-cm): 18 High Volt, Low Current Arc Resis (D495): -
IEC Ball Pressure (°C): 150 ISO Tensile Strength (MPa): - ISO Tensile Impact (kJ/m²): -	ISO Charpy Impact (kJ/m²): - ISO Heat Deflection @1.80 MPa (°C): 140 ISO Flexural Strength (MPa): - ISO Izod Impact (kJ/m²): -

Process Category: Material Extrusion Build Plane: Horizontal & Vertical Layer Thickness (mm): 0,2 Infill (%): - Post Processing Method: None For use with printer: MODEL 100, 200, 300	Printing Process Designation Number: <input type="text" value="1"/> Raster Angle (Degrees): 45/45 Print Speed (mm/sec): 20
---	--

Limited properties and ratings assigned to samples produced by the Additive Manufacturing technique representing a specific set of printing parameters and build strategy. Other print parameters and build strategies may result in significantly different results.

IEC/ISO small-scale test data does not pertain to building materials, furnishings and related contents. IEC/ISO small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 2019-10-01
 Last Revised: 2019-10-01



Example Blue Card, other information and ratings may be shown.



Flame Class – UL94

Tests for Flammability of Plastic Materials for Parts in Devices and Appliances, now harmonized with IEC 60695-11-10, 60695-11-20, ISO 9772 and ISO 9773. There are twelve UL 94 specified flame classifications assigned to materials based on the results of these small-scale flame tests.

HWI – Hot Wire Ignition

The test method for the determination of resistance to ignition of plastic materials from an electrically heated wire is described in the Standard ASTM D 3874.

HAI – High Arc Ignition

The HAI test determines a material's ability to withstand electrical arcing either directly on or just above the surface of the plastic material. This can occur in the presence of open switch contacts or in the event of the failure of an electrical connection.



RTI – Relative Thermal Index

The maximum service temperature for a material where a class of critical property will not be unacceptably compromised through chemical thermal degradation over the reasonable product lifetime. Electrical RTI is associated with critical electrical insulating properties. Mechanical impact RTI is associated with critical impact resistance, resilience and flexibility properties. Mechanical strength RTI or mechanical without impact is associated with critical mechanical strength where impact resistance, resilience, and flexibility are not essential.



CTI – Comparative Tracking Index

ASTM D 3638 (IEC 60112) Method: This test is used as a measure of the susceptibility of the material to tracking.

Dielectric Strength

The test method for the determination of the dielectric breakdown and strength of insulating materials, described in the Standard ASTM D 149 (IEC 60243).

HVTR – High Voltage Arc Tracking Rate

Test method to determine the susceptibility of the test material to track or form a visible carbonized conducting path over the surface when subjected to high-voltage, low-current arcing.

IPT – Inclined Plane Tracking

Described in the Standard ASTM D 2303, used as a measure of the susceptibility of a material to track.

Volume Resistivity

Testing according to ASTM D 257 (IEC 60167), procedures for the determination of d-c volume resistance, volume resistivity, surface resistance, and surface resistivity of electrical insulating materials.

High Voltage, Low Current Arc Resistance

Testing to ASTM D495, based on the number of seconds that a material resists the formation of a surface-conducting path when subjected to an intermittently occurring arc of high-voltage, low-current characteristics.



International Qualifications



Process Category

Definition of the 3D Printing technology:

- Material Extrusion
- Powder Bed Fusion Systems
- VAT Polymerization
- Material Jetting
- Binder Jetting
- Sheet Lamination
- Directed Energy Deposition



Build plane

The plane in which the samples are built, either horizontal or vertical.

Layer thickness

The thickness of one printed layer (in mm or microns).

Post processing method

Processing applied to the printed part after printing (eg. blasting, coating, electro-plating, etc.).

Specific to Material Extrusion:

Air gap

Shortest distance between two adjacent beads of the material (in mm or microns).

Print speed

The speed of printing (in mm/sec).

Raster angle

The angle of a printed layer relative to x-axis of the part (in degrees).

Specific to Powder Bed Fusion:

Hatch spacing

Distance between the adjacent hatch lines (in mm or microns).

Scan strategy

Scan strategy refers to the laser scan pattern used for performing the fusion. (Ex., Parallel Scans, Alternate Scans, etc.).

Scan Speed

Speed of the laser beam on the heated powder bed (in mm/sec).

Laser Power

Power value of the laser beam (in Watts).

Note: For some tests a Performance Level Category (PLC) may be assigned. This is typically a numeric rating from 0 – 5, where each number represents a range of property values, and 0 represents the best rating available.